

Date received: 26-04-12

Date of issue: 24-05-12

Report consists of 2 test reports.

Defects before testing: None

Sample name: PIKAIA verniciata in esterno

KRISTALIA S.R.L.
VIA CALDERANO 5
33070 BRUGNERA (PN)
ITALIA

TEST REPORT N° 140835

Overall dimensions: 490 x 500 x 830 (h) mm

List performed tests:

1. Seat and back fatigue test EN 1728:2000
2. Cross-cut test EN ISO 2409:2007



This document is validated by digital signature and time stamping in accordance with the Italian laws and the European Directives which regulate the electronic signature systems.

Managing Director
Dr. Andrea Giavon


The sample name and, when relevant, its description, are given by the orderer, and CATAS does not assume responsibility on this matter. This test report relates to the sample submitted for the test and no others. Additions, deletions or alterations are not permitted. This test report must always be reproduced in its entirety. Unless otherwise stated, sampling has been carried out by the orderer.

TEST REPORT N° 140835

Date of issue: 24-05-12
Sample weight: Not determined
Sample name: PIKAIA verniciata in esterno



Side view



Rear view



Bottom view

TEST REPORT**140835 / 1**

Date received: 26-04-12

Date of test: 09-05-12

Date of issue: 24-05-12

Sample name: PIKAIA verniciata in esterno

KRISTALIA S.R.L.
VIA CALDERANO 5
33070 BRUGNERA (PN)
ITALIA**Seat and back fatigue test EN 1728:2000**

Seat and back fatigue test, clause 6.7


Test results:

Seat force N	Back force N	Number of cycles	Remarks
1.000	300	200.000	No defects

Note:

The test has been carried out according to table 1 of EN 15373:2007, level 3 - severe.

This document is validated by digital signature and time stamping in accordance with the Italian laws and the European Directives which regulate the electronic signature systems.



Managing Director
Dr. Andrea Glavon

The sample name and, when relevant, its description, are given by the orderer, and CATAS does not assume responsibility on this matter. This test report relates to the sample submitted for the test and no others. Additions, deletions or alterations are not permitted. This test report must always be reproduced in its entirety. Unless otherwise stated, sampling has been carried out by the orderer.

TEST REPORT

140835 / 2

Date received: 26-04-12
Date of test: 22-05-12
Date of issue: 24-05-12



KRISTALIA S.R.L.
VIA CALDERANO 5
33070 BRUGNERA (PN)
ITALIA

Sample name: PIKAIA verniciata in esterno

Cross-cut test EN ISO 2409:2007

Sample preparation and conditioning: done by the customer.
Handy single blade cutting tool.

Test results:

Spacing between cuts	Classification 1st zone	Classification 2nd zone	Classification 3rd zone	Coating thickness
1 mm	0	0	0	from 0 to 60 μ m hard support
2 mm	0	0	0	from 0 to 60 μ m soft support
2 mm	0	0	0	from 61 to 120 μ m soft/hard support
3 mm	0	0	0	from 121 to 250 μ m soft/hard support

Classification:

- 0 no coating detached
- 1 less than 5% of coating detached
- 2 5-15% of coating detached
- 3 15-35% of coating detached
- 4 35-65% of coating detached
- 5 over 65% of coating detached

Notes:

- Chemical analysis of the tested material was not carried out.
- The test was carried out with all spacing cutting tools since the coating thickness was not measured.

COMMENTS NOT COVERED BY ACCREDITATION:

- Results obtained with 1 mm spacing cutting tool are more predictive of defects that may occur when in use.

This document is validated by digital signature and time stamping in accordance with the Italian laws and the European Directives which regulate the electronic signature systems.

Managing Director
Dr. Andrea Gravon

The sample name and, when relevant, its description, are given by the orderer, and CATAS does not assume responsibility on this matter. This test report relates to the sample submitted for the test and no others. Additions, deletions or alterations are not permitted. This test report must always be reproduced in its entirety. Unless otherwise stated, sampling has been carried out by the orderer.